

(168) 溶融 Fe-C 及び Fe-C-Si 合金中の炭素の相互拡散

九州大学工学部 O. 小野 陽一、瀬田兼彰

I. 緒言 溶融鉄合金中の諸元素の拡散に関する研究の一環として、溶融 Fe-C 合金における相互拡散係数を 1550°C において $0.5\sim4.0 \text{ wt\% C}$ の濃度範囲で測定し、拡散係数と炭素濃度との関係を求めた。さらに、溶融 Fe-C-Si(一定)合金中の炭素の相互拡散係数を 1550°C で測定し、炭素の拡散係数に及ぼす Si の影響を調べた。

II. 測定方法 測定には拡散対法を採用した。測定装置、測定操作及び拡散係数の決定法は既報^{1), 2)}のものと実質的には同じである。

III. 測定結果 測定結果をまとめて Table 1, 2 に示す。表には拡散対の濃度範囲も示してある。

(i) Fe-C 合金... 相互拡散係数 D は炭素濃度とともに増加し、両者の関係は次の実験式で表される。

$$D \times 10^4 = 0.84 + 0.25 \cdot [\text{wt\% C}] \text{ cm}^2/\text{s}$$

本実験の結果は Fig. 1 に示すように魚部らの

結果⁴⁾とかなりよく一致している。

(ii) Fe-C-Si(一定)合金... 炭素の主拡散係数 D_{CC} は 2 成分系の拡散係数 D よりも大きく、 $D_{CC}/D = 1.1\sim1.6$ である。すなわち、Si の添加によって、溶鉄中にあける炭素の拡散は速くなる。この結果は、Fig. 2 に示すように、魚部らの結果⁴⁾とも傾向としては一致している。

文献

- 1) 小野、松本: 金属学会誌, 37('73), p. 1344
- 2) 小野、瀬井: 鉄と鋼, 66('80), p. 601
- 3) 瀬田、小野: 鉄と鉄, 66('80), S156
- 4) 魚部、高井、小島、坂尾: 鉄と鋼, 66('80), p. 186

Table 1. Experimental results on the interdiffusion coefficient in molten Fe-C alloys at 1550°C .

Terminal compositions of couple (wt\%)		Diffusion coefficient $D \times 10^4$ (cm^2/s)
Upper sample	Lower sample	
1.01	0.51	1.00 (± 0.11)
1.50	0.55	1.12 (± 0.13)
2.04	1.07	1.17 (± 0.13)
2.41	1.49	1.32 (± 0.34)
2.93	1.93	1.57 (± 0.14)
3.35	2.35	1.47 (± 0.08)
4.01	2.97	1.68 (± 0.12)

Table 2. Experimental results on the main diffusion coefficient of carbon in molten Fe-C-Si alloys with approximately uniform silicon content at 1550°C .

Terminal compositions of couple (wt\%)				Diffusion coefficient $D_{CC} \times 10^4$ (cm^2/s)
Upper sample		Lower sample		
C	Si	C	Si	
2.09	0.98	1.08	1.03	1.37 (± 0.07)
3.04	1.05	2.03	0.98	1.92 (± 0.44)
1.95	1.93	1.02	2.06	1.67 (± 0.30)
2.89	2.00	2.02	1.93	2.26 (± 0.06)




Fig. 1 Interdiffusion coefficient in molten Fe-C alloy at 1550°C vs. carbon content of the alloy.




Fig. 2 The ratio of the main diffusion coefficient of carbon in molten Fe-C-Si alloy D_{CC} to the binary diffusivity in molten Fe-C alloy D at 1550°C vs. silicon content of the ternary alloy.