

(437)

硬鋼線材の衝風ミスト冷却法の検討

神戸製鋼所 中央研究所 (工博) 井上 肇 ○横山忠正 秋田章二
(工博) 山口喜弘 (工博) 高塚公郎

I 緒言

硬鋼線材の強度をコントロールする目的で、冷却媒体に衝風やミストを単独に用いる場合には、工業的規模でコントロールできるのは狭い範囲に限られる。そこで衝風ミスト(衝風とミストを混合したものでBMと略す)を利用した硬鋼線材の冷却について検討し、ミスト水量調節によりステルモア(SM)冷却並から鉛パテントング(LP)並までの強度を比較的容易にコントロールできることがわかった。

II 実験方法

衝風ミスト(BM)は、20~25 m/secの衝風の流れの中で、スプレーミストを発生させて、均一な空気とミストの混合流とし、実験室的に再加熱した硬鋼線材を冷却した。BMの水量密度を0~15 cc/cm²·minに変化させて、Table 1に示す線径の異なる各種線材を冷却して強度を調べた。

III 実験結果

1 ミスト水温の影響 - 5~25 °Cでは強度への影響は少ない(Fig. 1)。

2 各鋼種とも、水量密度を変化させることにより、SM並からLP並までの強度が得られる(Fig. 2)。

3 線材強度(TS: Kgf/mm²)は、重回帰分析の結果、水量密度(W: cc/cm²·min)、C当量(Ceq)、線径(d: mm)の関数として次式で表わすことができる。

$$TS = 10.9 + 112.7 C_{eq} - 1.38 (d - 5.5)$$

$$+ \begin{cases} 0.071 W^{0.07} d^{1.91} C_{eq}^{-2.66} & \dots \dots (1) \\ 0.102 W^{1.01} d^{0.90} C_{eq}^{-0.70} & \dots \dots (2) \end{cases}$$

TSは(1), (2)より求まる高い方の数値となる。

4 BM冷却すると、断面硬度分布は偏心する特徴がある(Fig. 3)。しかし、ほぼ同心円分布のLPと比較して、絞り、伸線特性にそん色はない(Fig. 4)。

Table 1 Chemical Composition (wt %)

Sample	Diameter	C	Si	Mn	P	S	Cr	Al	C _{eq} *
A	12 φ	0.80	0.26	0.83	0.021	0.006	0.05	0.088	1.049
B	9 φ	0.78	0.26	0.84	0.025	0.012	0.05	0.087	1.085
C		0.59	0.26	0.79	0.014	0.014	0.05	-	0.824
D		0.88	0.22	0.50	0.020	0.012	0.04	-	1.002
E	7 φ	0.75	0.28	0.49	0.018	0.010	0.04	-	0.907
F		0.65	0.22	0.75	0.014	0.018	-	-	0.858
G		0.80	0.24	0.50	0.015	0.012	0.04	-	0.971
H	5.5 φ	0.62	0.25	0.81	0.027	0.012	0.05	-	0.869
I		0.58	0.19	0.48	0.022	0.018	-	-	0.736

$$* C_{eq} = C + P + \frac{1}{5}(Mn + Si + Cr)$$




Fig. 1 Effect of water temperature on tensile strength of blast-mist-mixed (BM) cooled wire rod

Sample : A
Fig. 3 Crosssectional hardness distribution of BM cooled wire rod





Fig. 4 Comparison of reduction of area of BM cooled wire rod with that of lead patented wire rod




Fig. 2 Variations in tensile strength with water density of BM cooling