

(306) 160T複合吹鍊炉における炉内2次燃焼実機適用結果

(転炉熱補償技術の開発 第2報)

住友金属 和歌山製鉄所 森明義 永幡勉 加藤木健 ○市原清

本社 大喜多義道

1. 緒言

当所 160T-STB炉において、炉内2次燃焼実機適用試験を行なったので、以下に報告する。

2. 試験条件

独立な2系統の酸素供給ラインを有する特殊上吹きランスを用い、160T-STB炉において、Table1に示す条件により実機試験を行なった。

3. 結果

(1)着熱：2次燃焼による着熱効果は、Fig1に示す如く、 $F_{O_2-pc}/F_{O_2-tot}=11\%$ の条件で、溶銑率換算として3%が確認できる。これは前報⁽¹⁾15T炉の結果に対し、約70%の着熱効果に相当する。

(2)T-Fe: スラグのT-Feの上昇が懸念されたが、

Fig2に示す如くSTB操業と

大差はない。ただし2次燃焼適用によりスラグの Fe^{3+} が上昇することが特徴である。

(Fig3)

(3)脱P: Fig4に示す如く、2次燃焼適用により脱Pが促進している。これは2次燃焼の適用によるスラグの Fe^{3+} の上昇に関係があると考えられる。(Fig5) すなわち、2次燃焼によりガス相の酸素ボテンシャル($P_O_2 \cdot \alpha P_{CO_2}/P_{CO}$)が上昇し、それに見合ってスラグの酸素ボテンシャル(同一T-Feであっても Fe^{3+}/Fe^{2+} が上昇)が上昇するため脱Pが促進すると推定される。

4. 結言

160T STB炉において、炉内2次燃焼による着熱効果が確認できた。さらに大型炉への適用を図るとともに、将来予測される屑鉄事情に対処できる技術を確立したい。

[参考文献] 1) 岡村ら、本大会に発表予定

Table-1 Test Condition

Furnace		160 T - S T B
Lance	Type	Two independent flow Lance
	F_{O_2}	Main : 1.4~2.3 Nm ³ /min·T P.C. : 0.23~0.28 Nm ³ /min·T
	Jet Angle	Main : 10° × 3 holes P.C. : 30~35° × 6 holes
Lance Height		2.5~3.0 M
Bottom Stirring		0.04~0.05 Nm ³ /min·T
Exhaust Gas System		W. B type Half Boiler System




Fig.1 Thermal recovery effect of PC




Fig.2 Effect of PC on (T-Fe)




Fig.3 Effect of P.C. on Fe^{3+} in slag

Fig.4 Effect of P.C. on deposphorization

Fig.5 Relation between (Fe^{3+}) and $(P)/log(P)$