

## (217) 耐水素誘起割れ特性に及ぼす連鉄スラブV状偏析の影響

住友金属㈱和歌山製鉄所 ○人見康雄 友野 宏  
中手 博 山口洋治

## I 緒 言

連続鉄造スラブを素材とする原油、天然ガス輸送用ラインパイプの耐水素誘起割れ特性（以下耐HIC性）については、中心偏析の観点から種々報告され、化学成分（C, Mn, P）の影響についても明らかにされつつある。<sup>1)</sup>本報では、同様の観点から、既に報告した連鉄ブルームのV状偏析生成機構の検討によって得られた知見をもとに、<sup>2)</sup>連鉄スラブにおけるV状偏析の耐HIC性に及ぼす影響について調査したので報告する。

## II 試験方法

当所No.3CCにて、Table 1に示す条件で鉄造した2種類の鉄片厚スラブを対象に、スラブ段階での中心偏析、プレートの偏析と耐HIC性について調査した。

## III 試験結果

## (1) スラブ凝固組織と中心偏析

鉄片厚によって凝固組織は大きく異なり、それに対応して中心偏析形態も変化する。つまり、鉄片厚の増加とともに等軸晶化が促進され、中心偏析形態は、単一偏析線から複数のV状偏析線へと変化する。

(Photo.1, Fig.1, Fig.2)

## (2) プレート偏析と耐HIC性

上記スラブ段階での偏析線と対応してプレート板厚中心部のMn偏析はV状偏析の影響を受け、EPMA線分析によるMn偏析のピーク数は圧倒的に鉄片厚の大きい方で多くなる。また、この偏析に伴なうHICも増加する。(Fig.3, Fig.4)

これらは、いずれも連鉄スラブにおけるV状偏析に起因するものである。

## IV 結 言

連続鉄造スラブV状偏析の耐HIC性に及ぼす影響を明らかにした。

## (参考文献)

1) 村山、大谷、橋本、市橋、金子；  
鉄と鋼, 70(1984) S547

2) 杉田、友野、人見、浦、寺口、岩田、  
安元；鉄と鋼, 69(1983) A193

Table 1. Experimental conditions

Slab thickness	Chemical composition (%)					Superheat	Casting speed
	C	Mn	P	S	others		
210 mm	0.10	1.10	0.013	0.001	Nb-Ca	40~53°C	0.60 m/min
300						27~54	0.40




Photo. 1. Effect of slab thickness on center segregation




Fig. 1 Effect of slab thickness on solidification structure




Fig. 2. Effect of equiaxed zone thickness on V-shaped segregation




Fig. 3. Effect of slab thickness on Mn segregation




Fig. 4. Effect of slab thickness on C.L.R. in plate